



AN2000 ($\geq 99.9\%$)

2023.04.03

SPECIFICATIONS

▶ Chemical formula:	AlN
▶ Chemical name:	Aluminium nitride
▶ Apperance:	Dense sintered aluminium nitride
▶ Main characteristics:	High electrical insulation, high thermal conductivity, high purity, good plasma resistance
▶ Main applications:	Heat uniformity parts, high temperature treatment fixtures, semiconductor processing equipment parts
▶ Colour:	Ivory

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

Density		[g/cm ³]	JIS R 1634	3.2
Water absorption		[%]	JIS C 2141	0
Vickers hardness HV9.807N		[GPa]	JIS R 1610	11.2
Flexural strength 3 P.B.		[MPa]	JIS R 1601	220
Compressive strength		[MPa]	JIS R 1608	-
Young's modulus of elasticity		[GPa]	JIS R 1602	310
Poisson's ratio		[ν]	JIS R 1602	0.24
Fracture toughness (SEPB)		[MPa*m ^{0.5}]	JIS R 1607	-
Coefficient of linear thermal expansion	40 - 400 °C	[$\times 10^{-6}$ /K]	JIS R 1618	4.6
	40 - 800 °C	[$\times 10^{-6}$ /K]		5.2
Thermal conductivity		[W/(m*K)]	JIS R 1611	67
Specific heat capacity		[J/(g*K)]	JIS R 1611	0.72
Thermal shock temperature difference		[°C]	JIS R 1648	-
Dielectric strength		[kV/mm]	JIS C 2141	16
Volume resistivity	20 °C	[Ω^* cm]	JIS C 2141	>10 ¹⁴
	300 °C	[Ω^* cm]		10 ¹¹
	500 °C	[Ω^* cm]		10 ⁹
Dielectric constant		-	JIS C 2141	8.5
Dielectric loss angle		[$\times 10^{-4}$]	JIS C 2141	2
Loss factor		[$\times 10^{-4}$]	JIS C 2141	17

The values are typical material properties and may vary according to products configuration and manufacturing process.
For more details, please feel free to contact us.

KYOCERA Fineceramics Europe GmbH

E-Mail: info@kyocera-fineceramics.de · www.kyocera-fineceramics.de

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.