

SC1000

2023.04.03

SPECIFICATIONS

▶ Chemical formula:	SiC
▶ Chemical name:	Silicon carbide
▶ Apperance:	Dense sintered silicon carbide
▶ Main characteristics:	High temperature strength, high chemical resistance, excellent thermal conductivity
▶ Main applications:	Mechanical seal, high temperature resistance parts
▶ Colour:	Black

MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

Density		[g/cm ³]	JIS R 1634	3.16
Water absorption		[%]	JIS C 2141	0
Vickers hardness HV9.807N		[GPa]	JIS R 1610	23.0
Flexural strength 3 P.B.		[MPa]	JIS R 1601	450
Compressive strength		[MPa]	JIS R 1608	-
Young's modulus of elasticity		[GPa]	JIS R 1602	440
Poisson's ratio		[ν]	JIS R 1602	0.17
Fracture toughness (SEPB)		[MPa*m ^{0.5}]	JIS R 1607	2 ~ 3
Coefficient of linear thermal expansion	40 - 400 °C			3.7
	40 - 800 °C	[$\times 10^{-6}$ /K]	JIS R 1618	4.4
Thermal conductivity		[W/(m*K)]	JIS R 1611	200
Specific heat capacity		[J/(g*K)]	JIS R 1611	0.67
Thermal shock temperature difference		[°C]	JIS R 1648	-
Dielectric strength		[kV/mm]	JIS C 2141	-
Volume resistivity	20 °C			10^8
	300 °C	[$\Omega \cdot cm$]	JIS C 2141	10^4
	500 °C			10^3
Dielectric constant		-	JIS C 2141	-
Dielectric loss angle		[$\times 10^{-4}$]	JIS C 2141	-
Loss factor		[$\times 10^{-4}$]	JIS C 2141	-

The values are typical material properties and may vary according to products configuration and manufacturing process.
For more details, please feel free to contact us.

KYOCERA Fineceramics Europe GmbH

E-Mail: info@kyocera-fineceramics.de · www.kyocera-fineceramics.de

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.